

Thin Film Power Resistors



Product may not be to scale

The PWA series resistor chips offer a 500 mW power rating in a small size. These offer one of the best combinations of size and power available.


The PWAs are manufactured using Vishay Electro-Films (EFI) sophisticated thin film equipment and manufacturing technology. The PWAs are 100 % electrically tested and visually inspected to MIL-STD-883.

FEATURES


- Wire bondable
- 500 mW power
- Chip size: 0.030 x 0.045 inches
- Resistance range 0.3 Ω to 1 $\text{M}\Omega$
- Oxidized silicon substrate for good power dissipation
- · Resistor material: Tantalum nitride, self-passivating

APPLICATIONS

The PWA resistor chips are used mainly in higher power circuits of amplifiers where increased power loads require a more specialized resistor.



STANDARD ELECTRICAL SPECIFICATIONS				
PARAMETER				
Noise, MIL-STD-202, Method 308 100 Ω - 250 k Ω < 100 Ω or > 251 k Ω	- 35 dB typ. - 20 dB typ.			
Moisture Resistance, MIL-STD-202 Method 106	± 0.5 % max. Δ <i>R/R</i>			
Stability, 1000 h, + 125 °C, 250 mW	± 0.5 % max. Δ <i>R</i> / <i>R</i>			
Operating Temperature Range	- 55 °C to + 125 °C			
Thermal Shock, MIL-STD-202, Method 107, Test Condition F	± 0.1 % max. Δ <i>R/R</i>			
High Temperature Exposure, + 150 °C, 100 h	± 0.2 % max. Δ <i>R</i> / <i>R</i>			
Dielectric Voltage Breakdown	200 V			
Insulation Resistance	10 ¹² min.			
Operating Voltage Steady State 5 x Rated Power	100 V max. 200 V max.			
DC Power Rating at + 70 °C (Derated to Zero at + 175 °C) (Conductive Epoxy Die Attach to Alumina Substrate)	500 mW			
5 x Rated Power Short-Time Overload, + 25 °C, 5 s	± 0.1 % max. Δ <i>R</i> / <i>R</i>			



MECHANICAL SPECIFICATIONS in inches				
PARAMETER				
Chip Size	0.030 x 0.045 ± 0.002 (0.762 x 1.143 ± 0.5 mm)			
Chip Thickness	0.010 ± 0.002 (0.254 ± 0.05 mm)			
Chip Substrate Material	Oxidized silicon, 10 kÅ minimum SiO ₂			
Resistor Material	Tantalum nitride, self-passivating			
Bonding Pad Size	0.007 x 0.024 (0.1778 x 0.6096 mm)			
Number of Pads	2			
Pad Material	10 kÅ minimum aluminum			
Backing	None, lapped semiconductor silicon			

Gold back for eutectic die attach Options:

Gold bonding pads, 15 kÅ minimum thickness

Contact Applications Engineer

ORDERING INFORMATION								
Example: 100 % visual, 10 kΩ, ± 1 %, ± 100 ppm/°C TCR, aluminum pads, class H visual inspection								
W INSPECTION/ PACKAGING W = 100 % visually inspected parts in matrix tray per MIL-STD-883 X = Sample, visually inspected parts loaded in matrix trays (4 % AQL)	PWA PRODUCT FAMILY	900 PROCESS CODE See Process Code table	1000 RESISTANCE VALUE Use first 4 digits significant digits of the resistance	1 MULTIPLIER CODE D = 0.0001 C = 0.001 B = 0.01 A = 0.1 0 = 1 1 = 10 2 = 100 3 = 1000	F TOLERANCE CODE B = 0.1 % C = 0.2 % D = 0.5 % F = 1.0 % G = 2.0 % H = 2.5 % J = 5.0 % K = 10 %			

Document Number: 61019 Revision: 12-Mar-08





Vishay

Disclaimer

All product specifications and data are subject to change without notice.

Vishay Intertechnology, Inc., its affiliates, agents, and employees, and all persons acting on its or their behalf (collectively, "Vishay"), disclaim any and all liability for any errors, inaccuracies or incompleteness contained herein or in any other disclosure relating to any product.

Vishay disclaims any and all liability arising out of the use or application of any product described herein or of any information provided herein to the maximum extent permitted by law. The product specifications do not expand or otherwise modify Vishay's terms and conditions of purchase, including but not limited to the warranty expressed therein, which apply to these products.

No license, express or implied, by estoppel or otherwise, to any intellectual property rights is granted by this document or by any conduct of Vishay.

The products shown herein are not designed for use in medical, life-saving, or life-sustaining applications unless otherwise expressly indicated. Customers using or selling Vishay products not expressly indicated for use in such applications do so entirely at their own risk and agree to fully indemnify Vishay for any damages arising or resulting from such use or sale. Please contact authorized Vishay personnel to obtain written terms and conditions regarding products designed for such applications.

Product names and markings noted herein may be trademarks of their respective owners.

Revision: 18-Jul-08

Document Number: 91000 www.vishay.com